



中国认可
国际互认
检测
TESTING
CNAS L0690

TEST REPORT

Report No.: WT2022B01A04679

Shandong Chamboard Timber Material

Entrusted by:

Co.,Ltd.

Sample Name:

Chamboard JunZi Timber

Test Type:

Entrusted test

China Testing & Certification International Group Co.,Ltd.

National Research Center of Testing Techniques for Building
Materials



WT2022B01A04679


China Testing & Certification International Group Co.,Ltd.
National Research Center of Testing Techniques for Building
Materials

Test Report

Report No.: WT2022B01A04679

Page 1 of 2

Sample Name	Chamboard JunZi Timber	Test Type	Entrusted test
Entrusted by	Shandong Chamboard Timber Material Co.,Ltd.	Brand	JTL
Manufacture	Shandong Chamboard Timber Material Co.,Ltd.	Sample State	Meet the requirements of testing
Receiving Date	October 8, 2022	Quantity of sample	8 pieces
Production Date/ Batch number	——	Model/Size	140mm×500mm×20mm
Test Method	The method for the test items are detailed in the data page.	Test Date	October 10-28, 2022
Judgment Standard	GB/T 39600-2021 Formaldehyde emission grading for wood-based panel and finishing products		
Test Item	Formaldehyde emission		
Test Result	* After inspection, the test result of Formaldehyde emission meets the technical requirements of standard GB/T 39600-2021 Table 1 (Grade E_{NP}) Detailed conclusions are listed in the data page.* Date of issue: 2022-11-02		
Remarks: (Blank)			



Approved by 韩蔚 **Checked by** 陈鹏 **Compiled by** 王桂芳

Address: No.1 Guanzhuang Dongli ,Chaoyang District, Beijing, China
Tel: 00-86-10-51167681

P.C.: 100024

China Testing & Certification International Group Co.,Ltd.
National Research Center of Testing Techniques for Building
Materials

Test Report

Report No.: WT2022B01A04679

Page 2 of 2

No.	Test Item	Standard Limit Table 1			Test Result	Individual Conclusion	Test method
		Grade E ₁	Grade E ₀	Grade E _{NF}			
1.	Formaldehyde emission / (mg/m ³)	≤0.124	≤0.050	≤0.025	Not Detected	Accord with Grade E _{NF}	GB/T 17657-2013 4.60
(Blank)							
							
Remarks: 1. Test location: Yongshun. 2. Not Detected: Formaldehyde emission < 0.005mg/m ³ .							

End of the Report

Address: No.1 Guanzhuang Dongli, Chaoyang District, Beijing, China
Tel: 00-86-10-51167681

P.C.: 100024