



Chambroad timber decking maintenance

Chambroad timber decking maintenance

Chambroad timber materials is made of natural wood through the Chambroad Timber process to achieve high stability. When used in the outdoor, due to ultraviolet light and temperature and humidity changes, specifically the local weather, prompted by ultraviolet aging, the surface color of the decking will fade gray. With the repeated contraction and expansion of dimension the products will appear a small amount of cracks on the surface. But the chambroad timber likes high level hardwood, the surface returns original wood colour after maintenance. If you prefer gray, you can reduce the times of maintenance to let the wood age naturally.

Steps

Soak the decking with a cleaner for 10-20 minutes, use a brush to clean the surface stains, and subsequently rinse the surface stains of decking with plenty of water. If possible use a garden hose or high-pressure water gun (4 kg pressure), generally at a height of 80-90 cm or more, to clean the surface of the plate of dust and debris.

1. Decking surface naturally dry for 24 hours. the surface must be completely dry before applying the oil treatment.
2. Must be oiled in sunny days.
3. Use the brush to oil the surface of decking, 1L of waterbase oil can be coated plate 10-15 square meters. Oil is showing translucent white as start, but after 30 minutes, oil gradually adsorbed to the interior of the plate, showing the full transparent. After painting, please wipe off the excess oil at the longitudinal interface of the plate.
4. After maintenance, it needs take 12 hours for the surface to be dry, during oil drying should be avoided from contacting water and stepping on it.



Shandong Chambroad Timber Material Co., Ltd. | **Address:** Economic Development Zone, Boxing County, Shandong Province, China | **Email:** info.timber@chambroad.com

Remarks

1. Be sure to choose a sunny day for maintenance. It is recommended to maintain once a year.
2. Customers can choose the brand of oil that suits their preferences for maintenance according to the situation. It is recommended to use waterbase oil.
3. If there are serious cracks and debris on the deck surface near the swimming pool, it is recommended to add a sanding procedure. After the deck is clean and dry, use a sander with 80# to sand it. After vacuuming the dust, please use outdoor waterbase oil for better results.